



ISO 536	ISO 534	ISO 11475	ISO 2470-2	ISO 2471	ISO 8791-3	ISO 5629		ISO 287
Weight (gsm)	Bulk (cm ³ /g)	CIE Whiteness	ISO brightness (%)	Opacity (%)	Roughness Bendsen (ml/min)	Dynamic Stiffness MD (mN.m)	Dynamic Stiffness CD (mN.m)	Relative humidity (%)
70	1,23	130	93	93	250	0,25	0,10	40-50
80	1,23	130	93	94	250	0,30	0,13	40-50
90	1,23	130	93	96	250	0,40	0,15	40-50
100	1,23	130	93	97.5	250	0,65	0,25	40-50
115	1,23	130	93	98	250	0,90	0,40	40-50
130	1,23	130	93	99	250	1,30	0,50	40-50

* i valori espressi sono soggetti alle tolleranze stabilite dal produttore.