

| MAINE 1 FACE |                           |                |                   |             |                             |                             |           |                                     |                                     |  |
|--------------|---------------------------|----------------|-------------------|-------------|-----------------------------|-----------------------------|-----------|-------------------------------------|-------------------------------------|--|
| ISO 536      | ISO 534                   | ISO 534        | ISO 11475         | ISO 2471    | ISO 5629                    | ISO 5629                    | TAPPI     | ISO 5627                            | ISO 5627                            | ISO 535  |
| Weight (gsm) | Bulk (cm <sup>3</sup> /g) | Thickness (μm) | CIE Whiteness (%) | Opacity (%) | Dynamic stiffness MD (mN.m) | Dynamic stiffness CD (mN.m) | Gloss (%) | Beck Smoothness V <sup>90</sup> (S) | Beck Smoothness R <sup>90</sup> (S) | Cobb 60 S, V <sup>90</sup> (g/m <sup>2</sup> ) |
| 80           | 0.81                      | 65             | 118               | 88          | 11                          | 6                           | 66        | 800                                 | 2100                                | 22   |
| 85           | 0.81                      | 69             | 118               | 89          | 13                          | 7                           | 67        | 700                                 | 1600                                | 22   |
| 90           | 0.80                      | 72             | 118               | 89          | 14,6                        | 8,8                         | 67        | 880                                 | 2000                                | 22   |
| 100          | 0.81                      | 81             | 118               | 91          | 19,8                        | 12,2                        | 68        | 900                                 | 1750                                | 22   |
| 110          | 0.80                      | 87             | 118               | 93          | 24                          | 15                          | 68        | 750                                 | 1800                                | 23   |
| 120          | 0.80                      | 95             | 118               | 94          | 31                          | 19,4                        | 70        | 750                                 | 1600                                | 23   |
| 135          | 0.80                      | 107            | 118               | 96          | 42                          | 27                          | 70        | 700                                 | 1400                                | 23   |
| 150          | 0.81                      | 122            | 118               | 97          | 59                          | 38                          | 70        | 580                                 | 1050                                | 23   |

\* i valori espressi sono soggetti alle tolleranze stabilite dal produttore.