

PARADE LABEL A

Test climate 23° C, 50 % relative humidity, DIN EN 20 187 / All rights to improve quality due to technical modifications reserved

Form number: AA-PQM-029-01/A 09/2015

Revision: A 04/2015 ersetzt Revision - 07/2014

Property	Unit	Standard	Target value					
			70.0 ± 6.0%	80.0 ± 4.0%	90.0 ± 4.0%	100.0 ± 4.0%	110.0 ± 4.0%	120.0 ± 4.0%
Grammage	g/m ²	ISO 536	70.0 ± 6.0%	80.0 ± 4.0%	90.0 ± 4.0%	100.0 ± 4.0%	110.0 ± 4.0%	120.0 ± 4.0%
Thickness	µm	ISO 534	57.0 ± 5.0	66.0 ± 5.0	73.0 ± 5.0	82.0 ± 5.0	90.0 ± 5.0	99.0 ± 5.0
Tensile strength MD	N/15mm	DIN EN 1924-2	58.0 ± 15.0%	68.0 ± 15.0%	76.0 ± 15.0%	85.0 ± 15.0%	91.0 ± 15.0%	97.0 ± 15.0%
Tensile strength CD	N/15mm	DIN EN 1924-2	31.0 ± 15.0%	38.0 ± 15.0%	42.0 ± 15.0%	48.0 ± 15.0%	53.0 ± 15.0%	61.0 ± 15.0%
Surface roughness top side	µm	ISO 8791/4	0.70 ± 0.30	0.70 ± 0.30	0.70 ± 0.30	0.70 ± 0.30	0.70 ± 0.30	0.70 ± 0.30
Surface roughness reverse side	µm	ISO 8791/4	2.80 ± 0.50	2.80 ± 0.50	2.80 ± 0.50	2.80 ± 0.50	2.80 ± 0.50	2.80 ± 0.50
Whiteness (R457) top side	%	ISO 2470	98.0 ± 3.0	98.0 ± 3.0	98.0 ± 3.0	98.0 ± 3.0	98.0 ± 3.0	98.0 ± 3.0
Opacity (ColourTouch)	%	ISO 2471	82.0 ± 3.0	85.0 ± 3.0	87.0 ± 3.0	89.0 ± 3.0	91.0 ± 3.0	92.0 ± 3.0
Gloss Tappi 75° top side	%	Tappi T480	68.00 ± 5.00	68.00 ± 5.00	68.00 ± 5.00	68.00 ± 5.00	68.00 ± 5.00	68.00 ± 5.00
relative humidity	%	Tappi 502	50.00 ± 7.50	50.00 ± 7.50	50.00 ± 7.50	50.00 ± 7.50	50.00 ± 7.50	50.00 ± 7.50
Cobb (H2O) 60 s reverse side	g/m ²	ISO 535	22.00 ± 4.00	22.00 ± 4.00	22.00 ± 4.00	22.00 ± 4.00	22.00 ± 4.00	22.00 ± 4.00

* i valori espressi sono soggetti alle tolleranze stabilite dal produttore.